

## Test Report N° L 131/0112-1


DMG-Project N°: 1201-0115  
 Test item: Orzel-WILL INFILL Granulate 0,6 – 2mm  
 Date of receipt: 2012-01-31  
 Sample taker: Customer  
 Test start: 2012-02-01  
 Test end: 2012-02-06  
 Date of report: 2012-02-06

Laboratory-N°					12-10302
Sample name:					Orzel-WILL INFILL Granulate 0,6 – 2mm
Parameter	Test method	Unity	Limit of quantification	Requirements DIN V 18035-7	Test result
Dry residue	DIN 12880	%	0,1		99,3
EOX	DIN 38414-17	mg/kg	0,50	≤ 100	24,1
Leachate 48 h (water)	DIN 38414-4	-	0		
DOC	DIN 1484	mg/l	0,10	≤ 40 *	12,2
Zinc	EN ISO 11885	mg/l	0,02	≤ 0,5	0,07
Leachate 48 h (CO2 saturated water)	DIN 38414-4		0		
Lead	EN ISO 11885	mg/l	0,005	≤ 0,040	0,030
Cadmium	EN ISO 11885	mg/l	0,001	≤ 0,005	< 0,001
Chrome	EN ISO 11885	mg/l	0,002	≤ 0,050	< 0,002
Chrome (VI)	DIN 38405-24	mg/l	0,007	≤ 0,008	< 0,007
Mercury	ICP-OES	mg/l	0,0002	≤ 0,001	< 0,0002
Tin	EN ISO 11885	mg/l	0,002	≤ 0,050	< 0,002

\* with respect to EOX in the total assessment

The test results relate solely to the test items specified in the test report.  
 This report may not be reproduced in part without the permission of the Dr. H. Marx GmbH  
 Unless otherwise agreed, the samples are kept for three month.

The SBR Rubber granulate fulfill the environmental requirements according to DIN V 18025-7.

  
 ( Dipl.-Chem. A. Ewen )

**Dr. H. Marx GmbH**  
 Gewerbepark  
 Tel. 06821/97 18-0 · Fax 97 18 50  
 66583 Spiesen-Elversberg